

## N-BAK2 540597.286

$n_d = 1.53996$	$v_d = 59.71$	$n_F - n_C = 0.009043$
$n_e = 1.54212$	$v_e = 59.44$	$n_{F'} - n_{C'} = 0.009120$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.51387
$n_{1970.1}$	1970.1	1.51871
$n_{1529.6}$	1529.6	1.52385
$n_{1060.0}$	1060.0	1.52919
$n_t$	1014.0	1.52980
$n_s$	852.1	1.53234
$n_r$	706.5	1.53564
$n_C$	656.3	1.53721
$n_{C'}$	643.8	1.53765
$n_{632.8}$	632.8	1.53806
$n_D$	589.3	1.53988
$n_d$	587.6	1.53996
$n_e$	546.1	1.54212
$n_F$	486.1	1.54625
$n_{F'}$	480.0	1.54677
$n_g$	435.8	1.55117
$n_h$	404.7	1.55525
$n_i$	365.0	1.56221
$n_{334.1}$	334.1	1.56971
$n_{312.6}$	312.6	1.57660
$n_{296.7}$	296.7	1.58287
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.01662154
$B_2$	0.319903051
$B_3$	0.937232995
$C_1$	0.00592383763
$C_2$	0.0203828415
$C_3$	113.118417

Constants of Dispersion $dn/dT$	
$D_0$	$-1.45 \cdot 10^{-6}$
$D_1$	$1.10 \cdot 10^{-8}$
$D_2$	$4.89 \cdot 10^{-12}$
$E_0$	$5.16 \cdot 10^{-7}$
$E_1$	$3.05 \cdot 10^{-10}$
$\lambda_{TK}$ [μm]	0.164

Temperature Coefficients of Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T [10^{-6}/K]$			$\Delta n_{abs}/\Delta T [10^{-6}/K]$		
	1060.0	e	g	1060.0	e	g
-40/ -20	1.1	1.8	2.3	-0.9	-0.3	0.2
+20/ +40	1.0	1.7	2.3	-0.3	0.3	0.9
+60/ +80	1.1	1.8	2.4	0.1	0.8	1.4

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ (10mm)	$\tau_i$ (25mm)
2500	0.758	0.500
2325	0.831	0.630
1970	0.937	0.850
1530	0.994	0.984
1060	0.999	0.997
700	0.998	0.996
660	0.998	0.995
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.998	0.994
460	0.997	0.992
436	0.997	0.992
420	0.997	0.993
405	0.997	0.993
400	0.997	0.993
390	0.997	0.992
380	0.996	0.990
370	0.996	0.989
365	0.994	0.986
350	0.988	0.971
334	0.963	0.910
320	0.867	0.700
310	0.693	0.400
300	0.398	0.100
290	0.158	
280	0.040	
270		
260		
250		

Color Code	
$\lambda_{80}/\lambda_5$	32/28
(*= $\lambda_{70}/\lambda_5$ )	

Remarks

Relative Partial Dispersion	
$P_{s,t}$	0.2810
$P_{C,s}$	0.5382
$P_{d,C}$	0.3042
$P_{e,d}$	0.2385
$P_{g,F}$	0.5437
$P_{i,h}$	0.7695
$P'_{s,t}$	0.2787
$P'_{C,s}$	0.5817
$P'_{d,C'}$	0.2536
$P'_{e,d}$	0.2364
$P'_{g,F'}$	0.4826
$P'_{i,h}$	0.7630

### Deviation of Relative Partial Dispersions $\Delta P$ from the "Normal Line"

$\Delta P_{C,t}$	-0.0089
$\Delta P_{C,s}$	-0.0039
$\Delta P_{F,e}$	0.0004
$\Delta P_{g,F}$	0.0004
$\Delta P_{i,g}$	-0.0027

### Other Properties

$\alpha_{-30/+70^\circ C} [10^{-6}/K]$	8.0
$\alpha_{+20/+300^\circ C} [10^{-6}/K]$	9.0
$T_g [^\circ C]$	554
$T_{10}^{13.0} [^\circ C]$	550
$T_{10}^{7.6} [^\circ C]$	727
$c_p [J/(g \cdot K)]$	0.690
$\lambda [W/(m \cdot K)]$	0.920
$\rho [g/cm^3]$	2.86
$E [10^3 N/mm^2]$	71
$\mu$	0.233
$K [10^{-6} mm^2/N]$	2.60
$HK_{0.1/20}$	530
HG	2
B	1
CR	2
FR	0
SR	1
AR	1
PR	2.3